



ENHANCED REFLECTIVE 1507



RECOMMENDED FABRICS

100% Cotton, 50/50 Blends and some polyester. May also work on some tightly woven nylons.




INK APPLICATION

Enhanced Reflective 1507 can be printed as is, or when printing on nylon or tightly woven fabrics, Coupler 100 can be used for an extra bond




ADDITIVES

Coupler 100



SCREEN MESH

110-160t/in (43-63t/cm) monofilament recommended. Printing through a coarser mesh may reduce the reflective quality of the ink.



EMULSION

Any direct or indirect solvent resistant emulsion.



SQUEEGEE

60-70 Durometer
Sharp edge.



CURE TEMPERATURES

325°F (163°C) the entire ink film.



CLEAN-UP

Any eco-friendly plastisol type screen wash



PRODUCT PACKAGING

Quart, 1 gallon, or 5 gallon containers



STORAGE OF INK CONTAINERS

65° to 90°F (18°C to 32°C). Avoid storage in direct sunlight. Keep containers well sealed



SDS

Refer to SDS prior to use

FEATURES

AXEON™ Enhanced Reflective 1507 is a retro-reflective ink that contains light-reflecting microspheres and metallic flakes. When a print is exposed to a focused beam of light, such as that from a flashlight or an automobile headlight, it reflects or returns light back to the light source.

Enhanced Reflective 1507 can be used as a unique decorative tool to increase nighttime visibility of a printed design.

Enhanced Reflective 1507 appears as a conventional metallic silver shimmer ink under normal lighting conditions, but with the very enhanced attribute that it helps to increase the nighttime visibility of a printed design. Designs made with Enhanced Reflective 1507 may be applied to light or dark fabrics.

SPOT FLASHING

This product will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should be just dry to the touch, with no lift off, but not totally fused. Totally fusing the underprint may cause inter-coat adhesion problems with the inks printed on top. Final fusing or curing will occur in the dryer. Failure to fuse ink properly may cause cracking, poor adhesion and poor wash fastness.

APPLICATION

Ink may be used straight out of the container.

1. Stir or mix the Enhanced Reflective 1507 before each use. The reflective microspheres used in the ink will settle in the container when ink is stored for any length of time.
2. Enhanced Reflective 1507 is not a low bleed product and is not recommended for use on bleeding fabrics.
3. Wait 24 hours after printing and proper curing before washing finished product.

AXEON™ Enhanced Reflective 1507 can be mixed with Coupler 100 for extra adhesion when printing on nylon or tightly woven polyester fabrics or for ultimate wash durability. Coupler 100 can be obtained separately if needed and should be thoroughly hand stirred into the ink to the following proportions:

1 gram of Coupler 100 to 20 grams of ink (5% by weight)

Pot life of mixed ink is 8 to 12 hours. Do not mix more ink than is needed for a job. Do not under catalyze the ink. Over catalyzation will shorten pot life of ink.

IMPORTANT INFORMATION

For best results, product should not be modified with any viscosity reducers or thickeners. Viscosity of this product is already low and any modifications can result in poor reflective quality.

The retroreflective properties of Enhanced Reflective 1507 can be diminished by using an improper screen mesh, under-curing, by adding other inks, pigments or additives to the ink.

For best long term wash durability of printed fabric, machine wash finished product inside out in cold water, delicate cycle. Do not use bleach. Do not iron on printed area of garment. Recommend line or hang dry. The reflective quality of the Reflective product should improve after the first washing.

Test dryer temperatures and wash test printed product before and during a production run.

This ink and those in the **AXEON™** product line are not formulated with PVC resins or phthalate plasticizers, nor are they intentionally added.

Care should be taken to not cross-contaminate the **AXEON™ products with PVC or phthalate containing products.**

Do not use standard plastisol curable reducers with this or any of the **AXEON™ products.**

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.

REV. 260001