

RECOMMENDED FABRICS

100% Cotton
Some 50/50 Cotton/Polyester Blends




INK APPLICATION

Metallic Gold 92 should be used right from the container without any modifications. Stir well prior to each use.



ADDITIVES

Not recommended.




SCREEN MESH

74-160 t/in (30-63 t/cm) monofilament



EMULSION

Any direct or indirect emulsion or capillary film in the 35 to 70 micron range



SQUEEGEE

65-75 Durometer
Sharp edge



CURE TEMPERATURES

325°F (163°C) entire ink film



CLEAN-UP

Any eco-friendly plastisol screen wash



PRODUCT PACKAGING

Quart, 1 gallon, 5 gallon, 30 gallon or 50 gallon containers



STORAGE OF INK CONTAINERS

65° to 90°F (18°C to 32°C)
Avoid storage in direct sunlight
Keep containers well sealed



SDS

Refer to SDS prior to use

FEATURES

Metallic Gold 92 is used to produce a “gilded” metallic look when printed.

Metallic Gold 92 produces the best look when directly printed onto a garment or fabric.

Designs made with Metallic Gold 92 may be applied to light or dark fabrics.

SPOT FLASHING

This product will spot dry, with a very low after flash tack. Dwell time is dependent on the spot dryer used. In some cases, you may have to lower the heat of the spot cure unit because too much heat may actually make the ink tacky. When you spot dry, you are only partially fusing or gelling the surface of the ink. The ink should be just dry to the touch, with no lift off, but not totally fused. Totally fusing the underprint may cause inter-coat adhesion problems with the inks printed on top. Final fusing or curing will occur in the in the dryer. Failure to fuse ink properly may cause cracking, poor adhesion and poor wash fastness.

IMPORTANT INFORMATION

Caution: Metallic Gold 92 contains a high loading of uncoated metallic powders that will tarnish (turn gray) when exposed to any type of detergent or water that contains a bleaching or whitening agent. The abrasion resistance of this ink is low. There will be some rub-off of metallic particles even when the ink is properly cured/fused. It is extremely important to preprint and test printed fabrics for wash and wear durability before beginning production.

Metallic Gold 92 reflects infrared heat. A forced air dryer is highly recommended for proper curing/fusion of these products. Complete fusion of these products may be very difficult to achieve in an infrared dryer. Even when the Metallic Gold 92 is properly fused, there will be some rub off of metallic particles. Check for proper cure/fusion of product by wash testing finished product according to the wash instructions below.

To obtain best wash results, make sure printed inks are properly cured/fused and hand wash with a phosphate free detergent such as Woolite®, then air or line dry. Do not use bleach, iron or dry clean the printed garment.

Air drying washed product is strongly recommended. Dulling of ink surface may be caused by heat and abrasion in a clothes dryer.

Garments printed with Metallic Gold 92 should be labeled with recommended washing instructions.

It is recommended to use Gold Shimmer 157 when best overall wash and wear durability is desired for metallic looking prints.

LEGAL DISCLAIMER

Recommendations and statements made are based on International Coatings' research and experience. Since International Coatings does not have any control over the conditions of use or storage of the product sold, International Coatings cannot guarantee the results obtained through use of its products. All products are sold and samples given without any representation of warranty, expressed or implied, of fitness for any particular purpose or otherwise, and upon condition that the buyer shall determine the suitability of the product for its own purpose. This applies also where rights of third parties are involved. It does not release the user from the obligation to test the suitability of the product for the intended purpose and application.